

Specialty Lubricants

MOLYKOTE® HP 870 Grease

Fully fluorinated grease provides extraordinary performance under extreme conditions

FEATURES

- Compatible with most rubber and plastics
- Excellent stability at high temperatures
- Superior resistance to chemicals and solvents
- Minimal deterioration due to oxidation, appropriate for long-term lubrication
- Low vapor pressure (base oil)

COMPOSITION

- Perfluoro polyether
- Fluorinated polymer
- Corrosion inhibitor

APPLICATIONS

- MOLYKOTE HP 870 Grease can be used broadly under harsh conditions such as high temperatures, corrosive, solvent, liquefied natural gasses, high vacuum, etc.
- This grease is ideally used for use in clean rooms, semiconductor manufacturing equipment, cardboard manufacturing equipment, hot air dryer motor axles, etc., where the evaporation of the lubricant could be problematic.

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard*	Parameter	Unit	Value
	Appearance		White
JIS K 2220	Penetration (worked 60 times)	mm/10	280
	Service temperature range	°C	-20 to 250
	NLGI class		2
	Density	g/cm ³	2.0
MIL-S-8660	Bleed (200°C 24 hours)	%	5.0
MIL-S-8660	Evaporation (200°C 24 hours)	%	1.0
MIL-S-8660	Evaporation (200°C 1000 hours)	%	3.0
ASTM D 2596	Four ball weld load (1500rpm/1minute)	N	>4900
ASTM D 2266	Four ball wear scar (1200rpm, 392N, 1 hour)	mm	1.3
JIS K 2220	Low temperature torque test (-20°C)		
	Starting torque	Ncm	54
	Running torque	Ncm	28
JIS K 2220	Low temperature torque test (-40°C)		
	Starting torque	Ncm	Not measurable
	Running torque	Ncm	Not measurable
DIN 51 802	Emcor corrosion test		0 to 1
	Base oil vapor pressure 20°C	pa	2x10 ⁻⁶

*JIS: Japanese Industrial Standard.

ASTM: American Society for Testing and Materials.

MIL: Military Specification and Standards.

DIN:Deutsches Industrie Norm.

HOW TO USE

Clean points of contact. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

HANDLING PRECAUTIONS

Although MOLYKOTE HP 870 Grease is extremely chemically stable, it gradually begins to break down at temperatures in excess of 200°C releasing a toxic gasses; be sure that this product is only used in an environment with adequate ventilation. Do not smoke cigarettes if they have been in contact with this product. Be sure to wash your hands thoroughly after working with this product.

USABLE LIFE AND STORAGE

When stored, unopened in a cool, dark place this product, has a usable life of 36 months from the date of production.

PACKAGING

This product is available in 100g plastic cans and 750g collapsible cartridges.

CAUTION

1. Data included in this document are average values, not specification values. Any applications for this product given in this document are merely examples. Perform thorough evaluations to confirm functionality, effectiveness, and safety before use.
2. No guarantees are made that the applications described in this document are free from infringements of any patent.
3. This product was developed for industrial use, and is not intended for use in medical equipment, pharmaceutical products, etc.
4. Be sure to read the material safety data sheet (MSDS) and container label for this product before use.
5. Contact Dow Corning Asia, Ltd., before reproducing any data from this document.

WE HELP YOU INVENT THE FUTURE.™

www.dowcorning.com